

CHAPAS

Láminas en frío, caliente, decapadas, galvanizadas			
Espesores	Kg/m ²	Espesores	Kg/m ²
0,4	3,30	2,5	20,61
0,5	4,12	3,0	24,73
0,6	4,95	4,0	32,97
0,7	5,77	5,0	41,21
0,8	6,59	6,0	49,46
0,9	7,42	7,0	57,70
1,0	8,24	8,0	65,94
1,2	9,89	10,0	82,43
1,5	12,36	12,0	98,91
2,0	16,49		

Otras chapas Estriada, lagrimada			
Espesores	Kg/m ²	Espesores	Kg/m ²
3,0	30,56	8,0	74,24
4,0	38,75	9,0	81,59
5,0	50,09	10,0	88,20
5,5	53,45	12,0	104,69
6,0	57,54	14,0	121,17
7,0	65,73	15,0	137,66

