

CHAPAS

| Láminas en frío, caliente, decapadas, galvanizadas | | | |
|---|-------------------------|------------------|-------------------------|
| Espesores | Kg/m² | Espesores | Kg/m² |
| 0,4 | 3,30 | 2,5 | 20,61 |
| 0,5 | 4,12 | 3,0 | 24,73 |
| 0,6 | 4,95 | 4,0 | 32,97 |
| 0,7 | 5,77 | 5,0 | 41,21 |
| 0,8 | 6,59 | 6,0 | 49,46 |
| 0,9 | 7,42 | 7,0 | 57,70 |
| 1,0 | 8,24 | 8,0 | 65,94 |
| 1,2 | 9,89 | 10,0 | 82,43 |
| 1,5 | 12,36 | 12,0 | 98,91 |
| 2,0 | 16,49 | | |

| Otras chapas | | | |
|----------------------------|-------------------------|------------------|-------------------------|
| Estriada, lagrimada | | | |
| Espesores | Kg/m² | Espesores | Kg/m² |
| 3,0 | 30,56 | 8,0 | 74,24 |
| 4,0 | 38,75 | 9,0 | 81,59 |
| 5,0 | 50,09 | 10,0 | 88,20 |
| 5,5 | 53,45 | 12,0 | 104,69 |
| 6,0 | 57,54 | 14,0 | 121,17 |
| 7,0 | 65,73 | 15,0 | 137,66 |

